Record Group 104. Entry 28.

Assays of Ores, Jewelry, Plate &c. not deposited:
and moneys received therefor.
Commencing July 1, 1878. No. IV.

Digitized September 12, 2023, Philadelphia, Pennsylvania.
Box 1, Book 1, for 1878-79.

Note: Lightly printed and written text may be difficult to read in scanned version. Hidden words might be visible on the original pages. Larger (18+ inch) documents are scanned in multiple parts. Correspondence organization is presented as stored and is not always in chronological order.

RG 104 RECORDS OF THE BUREAU OF THE MINT

Records of the U.S. Mint at Philadelphia
Operating Records
Records of the Assays

ASSAY WORKBOOKS, 1795-1905

Box 1 NC-152 Entry 28

Assays of

Ores. Jewelry, Plate &c.

not deposited:

nd moneys received therefor.

Commencing July 1. 1878

No. IV.

July 1878

July 6th From Bailey, Banks and Biddle, a sample link of Gold Chain

Fineness .557.— or 13 12/32 K
Charge $1. Paid

July 6th From Bailey, Banks & Bidde a Silver Spoon marked Sterling

Fine 913½
Charge $1. Pd.

July 10. From N. R. Bartleson, Macomb, Illinois, two samples of ore.

Trace of silver in each.

Rec'd $10.—

July 13. 1878 From S. B. Hagstoz, Philad^{a}. – a sample of rock.

Contains no gold, or silver.

Rec^{d}. $5. —

July 16 – 1878 From Bailey Banks & Biddle Silver Knives & Spoons.

(Knife)	No 1	932
"	" 2	925
Spoon	" 3	925
"	" 4	926
"	" 5	924

Rec^{d}. $5.00

July 19. From W. A. Schäfer, Phila. two samples of bracelet-strips, or bands of gold & silver welded together. Required to know the fineness of each, & the values through.

No 1, gold side 708; or 17 kar.
" silver " 888.
Cut through, gold 290, silv. 580.
Total val. per oz. $6.58

No 2, gold side 584; or 14 kar.
" silver " 780.
Cut through, gold 233, silv. 554.
Total val. per oz. $5.47.
The outside assays were from scrapings.

Rec'd $5.—

(Duplicate.) Rec'd from the Assayer, twenty seven dollars, for the month of July.

$27.— Jas. Pollock Supt

September 5th Received from Simons, Bros & Co. A sample of Gold

Fineness 590. or 14. 5/32 Kar

Recd. $1.—

Septr 10th From Simons, Bros & Co. small lump of Gold.

Fineness 890 1/2 or 21 11/32 Kar

Recd. $1.—

Sept. 18. From Drs Roop & Dunham, Ashland, Ohio.

a black mineral — carbon & silex.

No gold or silver.

Recd. $5.—

Sept. 20 From Webb & Hall, Janesville, Wisconsin; a gold ring.

Fineness 722, = $17\frac{10}{32}$ Kar.

Rec'd $1.—

Sept. 26 From Roberts & Barnard 32 Ruth St. Rushville, Indiana, a gold ring.
After melting, 379 = $9\frac{3}{32}$ Karats.

Rec'd $1.—

Oct. 15th Crushed Ore from Dr. Foster.
Gold 1½ Ozs per ton
Silver 2 " "

Rec'd $5.—

October 31. Received from the Assayer, nine dollars for the month of September
$9.—

Jas. Pollock
Supt.

Oct. 17. 1878 From Bailey, Banks, & Biddle, Philade.

Piece of chain
Fineness 515, = $12\frac{12}{32}$ k.

Recd. $1.—

Oct 19. From Paul Mockenhaupt, 148 State St. Chicago, gold watch-case.

Outer lid, 512 thous. = $12\frac{9}{32}$ Kar.
Inner " 455 = $10\frac{30}{32}$ "
Rim 405 = $9\frac{23}{32}$ "

Recd. $1.—

Oct 25. From Simons Bro. & Co. Phila. a slip of fine silver, rolled.

Fineness 999½, two assays.

Recd $1.—

Nov. 7. From W.B. Clapp, Young & Co. 149 State St. Chicago.
Three pieces of gold chain.

No. 1, 5 16 thous = 12 $\frac{12}{32}$ K.
2 493½ " 11 $\frac{27}{32}$ K.
3 499½ " 12 nearly

Rec'd. # 3. —

Nov. 7. From T.B. English, Treas'r. of Candelas Mining & Smelting Company of Mexico, two large buttons for assay.

No. 1, weight after melting, 6.05 ozs
Gold 748½. Silver 145.

No. 2 wt. after melting 4.31 ozs
Gold 124½. Silver 712.
Bars stamped accordingly, & returned.

Rec'd. # 3. —

Nov. 14. 1878 From P. A. Snell,
silver containing gold.
After melting, 25 b. 8 b oxs.
Contains silver 730
" gold 46½
Stamped Returned.

Rec'd $1.50 for assay.
" 1.35 additional, melting,
$2.85. 15 cts. added, makes 3.00

Nov. 20. From Capt. James Flovington,
U.S. Consul at Aspinwall.
(Care James E. Morris, 165 Chambers St. N.Y.)
four specimens gold ore, from S. America.

No. 1.	2½ oxs.	per ton.	$52.—
2.	Trace		
3.	½ oz	"	$10½
4	1 oz	"	$20½

Rec'd $20.—

Nov. 22. From Corbin & Goodrich,
430 Walnut St. Phila.a
Seven samples of ore, from Arizona.

No. 1	Silver,	25 ozs.	per ton 2000 lb	
2	"	15	"	"
3	"	105	"	"
4	"	360	"	"
5	"	20	"	"
6	"	35	"	"
7	"	15	"	"

Orion

Traces of gold only.

Rec.d $35. —

Dec. 6. From Dr. T. A. D. Foster.
A Button, ~~contains~~ weighing 21 lb gr
Contains G. 71, S. 190. C &c. 739.
Or, in grains, G 15.3, S. 41. C &c. 159.7

Sample of Crushed ore: 0.7 oz.
Gold, say $14.60 per ton; Silv. 0.9 oz.
(per ton.) From N. Carolina.

Rec.d $6.00

Dec 13. 1878. From Webb & Hall, Janesville, Wisconsin, a piece of gold jewelry.

Fineness 736. = $17\frac{21}{32}$ K.

Rec'd. $1.—

Dec 16. From Dr. J. A. L. Forster, a sample of ore in powder.

Contains Silver, 7 ozs. per ton. 7.00
" Gold $\frac{1}{4}$ oz. " 5.—
12.—

Rec'd. $5.—

Dec 19. From Corbin & Goodrich, sample of ore, "american Mine" Arizona.

Contains Silver, 87 ozs. per ton.
Trace of gold.

Rec'd. $5.—

January 10, 1879 Received from the Assayer, eighty nine dollars for the months of October, November & December, 1878.

$89.—

Jas. Pollock
Supt.

Jany 13. From Corbin & Goodrich, sample of ore, "Golden Gate" mine, Arizona.

Contains 32 oxs. silver per ton.
No gold.

Rec'd. $5.—

Jany 18. 1879 From W. M. Viser & Co.
226 Eddy St. Providence R. I.
A sample of cocus polishing dust.
300 grs. yield, Gold 13.34 grains
" " Silver 4.23 "
Equal to, Gold 311 grs. per lb.
" Silver 99 " "
Rec'd. #1. —

Jany 24. From Corbin & Goodrich,
sample of ore from Arizona.

Contains silver, 72½ ozs. per ton.

Rec'd. #5. —

Jany 27. From Paul Mockenhaupt
148 State St. Chicago.
Two watch-cases.

No. 8019, 829½ fine.
" 67,820 864½ "

Rec'd. #2.00

Feb. 8. 1879 From Handy & Cronise, N. Y. – three samples –

	Silver	Gold	
1	980	13.0	not enough for duplicates
2	981	13.2	
3	980 3/4	13.0	

Rec'd $3.00

Feb. 25. From W. M. Vandever, Wilmington, Delaware, two specimens of gold ore from N. Carolina, near Charlotte.

No. 1. (pyrites) 2½ ozs. gold per ton

No. 2 (oxide of iron) 2 ozs. "

Rec'd $6.—

Feb. 26. From P. A. Snell, a ~~bar~~ metallic mixture, for assay.
(From an amalgamation of N.C. sulphides.)
Contains gold, 120
Silver 85
Copper &c. 795
1000

ozs.
Col. 39.42

value — g. 97.78
s. 3.65 (3.35 ozs)
Rec'd. 1.50 #101.43

March 4. From Thos. Mac Callum, William Leffers & — Wolf, Elmira, N.Y. a box of minerals.
Carb: lime, oxide of iron, & pyrites.
no gold or silver

Rec'd. #5. —

March 19. From I. A. Skadan, Weedsport, Cayuga Co. N.Y.

A sample of rock & powdered earth

Contains no gold, nor silver.

Rec'd. $5. —

March 28. From Corbin & Goodrich Tombstone District, Arizona —

Contains silver 304 ozs. per ton
no gold

Rec'd. $5. —

(Duplicate.) Received from the Assayer $38.50 the foregoing items for first quarter of 1879

R. Loudon Thrasher
U.S. Supt.

April 2. 1879 From Hon:
Stephen W. Downey, of Wyoming Terr.
a lot of gold amalgam (said to be
from Keystone mine) to be melted,
assayed, & returned.

	ozs
Weight after melting,	92.69
Fineness	829½
Silver	130

Gross Value – Gold $1589.19
Silver 12.52

From which the charges, $4.21 will
be deducted, if returned to be coined.
Rec'd. 1.50.

April 5. From Saml N. Moseley
Edgemore, New Castle Co. Delaware,
(Care of Harry Beeson, address.)
Quartz from Rapahannock Va.

Contains no gold

Rec'd $3.00

April 5. 1879 From Hon. M.S. Quay, a mineral from Colorado.

Contains a trace of silver; no gold.

$3.00 Recd. Aug 29th 1879.

April 5. From Capt. James Thorington, U.S. Consul, Colon-Aspinwall, S. America.
Four mineral specimens.
Contain only a trace of gold.

Rec'd #12.—

April 5.
From J.C. Galbreath, a specimen of minerals, from Callensburgh, Clarion Co. Penna.

Not assayed.

Rec'd #5. Returned.

April 7. From E. A. Corbin, Philad^a. a sample of native Chloride of silver from Arizona.

Contains Silver 10,405 ozs. per ton.
" Gold 25 " "

Rec^d. $3. —

April 18. From E. A. Rollins, through the Superintendent.

Lead ore, from Leadville, Colorado.

Gold 4/10 oz. say $8 per ton.
Silver 9½ ozs. say $10 "

April 21. From Hugh B. Wellman, Catlettsburg, Ky. an ore supposed to be tin; with a sample of the metal.

The ore is iron; without any tin; the metal is tin with a little lead; simply an artificial solder.

April 25. 1879 From Simons, Bro. & Co. Phila. -

Two samples of gold -

1. Fineness $992\frac{2}{10}$

2 " $524\frac{4}{10}$ ($12\frac{19}{32}$ Kar.)

Rec'd. #2. —

April 28. From Surgeon Geo. E. H. Harmon, U. S. Naval Academy, Annapolis.

Iron Ore. No gold, nor silver.

Rec'd #3. —

April 28. From Major Charles S. Mitchell, Fort Lyon. Colorado.

Contains $\frac{2}{10}$ oz. gold.
1 oz. silver.

Rec'd #5. —

May 3. From I. Welf, Cleveland, Ohio, two samples of gold.

B. 468 thous = $11\frac{8}{32}$ K.
R. 463 " = $11\frac{4}{32}$

Rec'd #2.—

May 14. From Robert Scott, Phila. — Gold Chain

Fine 538½ = $12\frac{30}{32}$ Karats

Rec'd #1.—

May 26. From Geo. W. Ross, Knoxville, Tenn. a mineral Specimen from "Smoky Mts. near N. Carolina line".

Contains no gold.

Rec'd #5.—

June 6. 1879 From I. P. Fletcher,
Ridge Farm, Vermilion Co. Illinois

Contains no gold, nor silver.

Rec'd # 3. –

From Geo. A. M. Barrett, Rockport
Knox Co. Maine.
A sample of mineral –
Contains no gold, nor silver.

Rec'd # 3. –

June 17. From Carrow Bishop & Co.
a sample of rolled gold. (Phila'a)

Fineness 977. = $23\frac{14}{32}$ kar.

Rec'd # 1. –

June 18. From N. B. Wellman, Catlettsburg, Ky. another sample of his ore.

Carb. lime, quartz &c with 40 pcs sesquiox. iron. No zinc, tin, or nickel (as he expected there was.) No gold or silver.

Rec'd $5.—

June 24. From Carrow, Bishop & Co. Philad'a- a sample of rolled gold.

Fine $993\frac{1}{2} = 23\frac{27}{32}$. K.

Rec'd. $1.—

June 26. From the same—

Fine $992\frac{1}{2} = 23\frac{26}{32}$ K.

Recd $1.—

June 30. From Geo. E. Coolidge, silver melted & assayed; not deposited Wt 145.32 ozs. Fine 998. no gold.

Rec'd. $1.50

(Duplicate.) Received from the Assayer, fifty three Dollars, the sum of the items for second quarter of 1879. $53.—

A. London Simmons
Supt

July 1. 1879. From George F. Harkness (office of G. & M. Barrett) Rockport, Knox Co. Maine

Contains a faint trace of silver.

Recd #3. —

July 1. From James Craven, 52 Mill St. Germantown, Pa. two samples of rock from Worcester Mass. —

Contain no gold, nor silver.

Recd #5. —

July 2. From Simons. Bro. & Co. Philad.a a sample of gold.

Fineness 560÷2, = 13 15/32 Kar.

Recd #1. —

July 3. 1879 From I. Logue, Currency Bureau, Treasury Dept., a mill sample (crushed) from California.

Contains Silver, 137 ozs. per ton.
Trace of gold.

Rec'd $3.00

July 9. From Simons, Bro's & Co. a sample of base gold —

Contains gold 212 thous. = $5\frac{3}{32}$ kar.

Rec'd $1.—

July 12. From Henry G. Taylor, Topeka, Kansas, a gold chain.

Wt. net 1.46 Fine 391 = $9\frac{12}{32}$ kar.

Rec'd $1.—

July 12. From Wm. S. Merriman, Morgantown, Indiana, a sample of gold grains.

Wt. 0.92. after melting 0.89 oz.

Fine 911.—

Rec'd. #1.—

July 14. From Carrow Bishop & Co. a sample of fine gold.

Fineness 997½ thous.

Rec'd. #1.—

July 14. Assay of two samples of ore, from R. Topham (thro' the Coiner.)

1. "Hercules"— silver 16 ozs. per ton
gold 1 " "
2. "Jupiter" silver 3 ozs. "
gold ½ " "

Rec'd. #3.—

July 18. 1879 From A.L. Maxwell, Knoxville, Tenn. four samples of ore.

No gold, nor silver

Rec'd #12.—

From T. Marshall, Philad^a
Silver ore from Tombstone District, Arizona.

Silver 8110 ozs. per ton of 2000 lbs
Gold 53 " " "

Small bar made from the ore, & stamped,
S. 980½ G. 6½.

Rec'd. $3.00

August 8. From P. W. Rider, Delphos, Allen Co. Ohio, a mineral sample.

Contains no gold, nor silver.

Rec'd $3.—

August 9th From Simons Bro & Co a sample of base Gold

Contains Gold 336½ thou = 8 1/16 K

Rec'd $1.—

Augt 13 From the same—

No. 1 478½ = 11 15/32 K

2 491½ = 11 25/32 K.

Rec'd $2.—

Augt 14 From the same

Fine 988.—

Rec'd $1.—

Aug. 14. 1879 From Carrow Bishop & Co. a sample of gold amalgam.

Fineness 826.

Rec'd $1.—

Augt. 18. From Simons Bro & Co.

No. 1 516½ = 12 12/32 K

2 530 = 12 23/32

3 986

Rec'd. $3.00

Augt. 19 From Simons Bro. & Co.

No. 1 546 = 13 3/32

2 527 = 12 21/32

Rec'd $2.—

Augt. 25. S. Carolina medal, "
from Mr Cochran. "Palmetto Regiment"
Wt. 75.41 grams, or 2.42 ozs.
Sp. gr. 17.60 (silver alloy)
Fine 880. Val per oz. $18.20

Aug. 26. From Simons Bro & Co.
No. 1, 993.
2 547½ = 13 4/32 kar.
Rec'd. $2.—

Sept. 2. From Simons Bro & Co.
sample of gold
Fineness 991.
Rec'd $1.—

Sept 5. From the same.
Fineness 992.
Rec'd. $1.—

Sept. 10. – From Simons Bros & Co
Two Samples of Gold.

No. 1 – 526 or $12\frac{20}{32}$

" 2. 538 $12\frac{29}{32}$

Recd #2.

Sept. 15. From the same –

Fine 719. = $17\frac{8}{32}$ K

Rec'd #1. –

Sept. 17. From Webb & Hall
Janesville, Wisconsin – sample of gold.

Fine 723. = $17\frac{11}{32}$ K

Rec'd #1. –

Sept. 22. From D. M. Myers, Mechanicsburg
Pa. Quartz, with carbonate of lime.
No gold, nor silver.

Rec'd #3. –

Sept 24. 1879. From Simons, Bro & Co. Philad^{a}.

No. 1 (rolled) 990 $\frac{3}{4}$

No. 2 (granulated) 990 $\frac{1}{2}$

Rec^{d} # 2.—

Sept. 26. From L. P. Carpenter, Germania, Alabama thro' the Director of the Mint— a mineral sample, containing so gold or silver

Rec^{d}. # 3. —

Sept. 27 From Hagstoz & Thorpe, Phil^{a}. two samples of gold—

No. 1. 988 $\frac{1}{2}$

2 994

Rec^{d}. # 2.—

Phila.

Sept. 30. 1879 From G. F. Blum, ir
two links of a gold chain.

Fineness 315, or $7\frac{18}{32}$ K.

Rec'd. $1.—

Received from the Assayer of the Mint, sixty seven dollars, the sum of the items for third quarter of 1879.

$67.— London Snowden
Supt.

October 2. 1879. From Messrs Simons Bro. & Co., sample of gold.

Fine 723½, = 17 12/32 kar.

Rec'd. $1.—

Oct. 3. From Dr. J. E. Means, Phila'a. two samples of ore from Black Hills, Dakota.

No. 1, gold 5½ ozs. $113. per ton
Silver 2 ozs. "

No. 2. gold 1 oz. $20⅔ per ton
Silver ½ oz.

Rec'd $6.—

Oct. 4. From Simons, Bro. & Co. a sample of gold

Fine 854 = 20 16/32 K.

Rec'd. 1.—

October 14. 1879 From Geo. P. Ayres, of Utah, two samples of ore.

No. 1. C.S.M, Gold 1½ ozs. per ton
Silver 2½ "

No. 2. C.S.D. Gold 1 oz.
Silver 3 "

Rec'd $6.—

October 16. From Orion Silver Mining Co., three samples.

No. 1. 71 ozs. Silver per ton.
2 174 " " "
3 25½ " " "
a trace of gold.
Rec'd. $9.—

Oct. 22. From Simons, Bro. & Co.

No. 1, 721 = 17 10/20 kar.
2 255 = 6 4/20 "

Rec'd. $2.—

Oct. 29 From Simons Bro. & Co

Granulation –
Fine 696½ = 16 23/24 K

Rec'd $1. –

Octr 29. From Geo. M. Woodward, Phila. a sample of gold.

Fineness 881½.
Rec'd $1. –

Nov. 11. From N. B. Alexander, Colorado – through E. W. Alexander, Supt. of mails, Philad'a. P. O.

Ore in powder.

No gold, or silver.

Rec'd. $3. –

Nov. 14. 1879 From Simons, Bro. & Co.

No. 1 990
2 681 = ~~16~~ 15 $\frac{11}{32}$ K.

Rec'd $2. —

Nov. 15. From W. M. Fisher & Co. Providence R.I. a piece of chain.

Fine 372. = 8 $\frac{30}{32}$ K.

Rec'd $1. —

Nov. 17. From Orion silver mining Co. —

Silver 49 oxs. per ton.
Trace of gold.

Rec'd. $3. —

Nov. 18. From Mrs. I. Ashbrook, 27 S. 4th St. Phila. — a mineral sample, "No. 1." — Contains silver 1½ oxs. per ton no gold.

Nov. 19. From Simons, Bro. & Co. Phila.a, a piece of gold.

Fineness 750 thous.
Rec.d $1.—

Nov. 20 From Booz & Thomas, 108 S 8th St. Phila.— a gold ring.

Fine 715, = $17\frac{5}{32}$ k.

Rec.d $1.—

Nov. 22. From I. Long, a sample of ore from the Black Hills, Dakota.

Gold, 7½ to 8 ozs. per ton. Two assays. say $160.—

Rec.d $3.—

Nov. 28. From Simons, Bro. & Co. gold granulated.
Fineness 995.

Rec.d $1.—

Nov. 28. 1879 A bar of lead from the Director, through the Supt.

Contains Silver 21 parts per thousand
" Gold $\frac{1}{3}$ of 1 part "
Weights - before melting 136.55 ozs. after, 82.65
1.93 st. silv. 0.03 st. gold

Nov 28. A small cake of silver containing gold, from Wm. S. Ringgold, through Mr Steel, ass't Coiner

Contains Silver 713 thous.
" Gold 282 "
Weight of the Cake, before cutting off the Assay, 1.77 ozs.
Rec'd #1.50.

Dec 1. From C.W. Jones, No. 18 N Third St Philada. 3 samples from New Mexico.

Contain a faint trace of silver only.

Rec'd #9.

Dec 2. Thro' the Superintendent, two specimens from O. J. Averell; Bingham canyon, Utah. —
P.O. Address. Salt Lake City.
No. 1, "Evergreen"
Silver 126 ozs per ton, 138. —
Gold ½ " 10.
$148.

No. 2, "Mayflower"
Silver 255 ozs. 280.
Gold $1\frac{3}{4}$ " 35.
315.

Rec'd $6. —

Dec 2. From Lloyd B. Wilson 24 Portland Block, Chicago, ore of "Chicago-Virginia Gold Mining Co." Orange Co. Va.

Gold $\frac{1}{10}$ oz. per ton.
Trace of silver.

Rec'd $3. —

Dec 4. 1879 From D. B. Horton,
of Wells. Fargo & Co. (thro' Adams Expres)
six samples of silver.

1	999¼
2	999¼
3	999¼
4	999
5	999
6	999

Rec'd. $6. —

Dec 6. From Orion Co. Arizona —

Silver, average of 4 assays, 2466 ozs.
Gold 1 oz. to 1 ¾ ozs.

Rec'd $3. —

Dec. 10. From S. W. & W. E. Vernon,
Stanford, Kentucky.

A mineral, containing no gold or silver.

Rec'd $3. —

Dec 10. From J. Elwood Vail, Forest Hill, Hanford Co. Md.

No gold, nor silver.

Rec'd. $3.—

Dec 27. From Director of the Mint, for the Treasury Dept. ore stated to be from Lerdo Mexico.

Contains silver 54 ozs. per ton.

Received from the Assayer of the Mint, seventy six dollars 50 cents, the sum of the items for the fourth quarter of 1879. $76.50

Gordon Norris
Superintendent

1880.

Jany 7.

Native gold, brought by Alexander Kay, for melting & assay, to be returned in the bar:

Weight after melting 88.57 ozs
Gold 831.
Silver 119.

Value of the gold 1521.52
" Silver 11.71

Recd. #2.—

Jany 9. From William Beeson, Dunbar, Fayette Co. Penna. a sample of ore in powder.

Contains no gold, nor silver.

Recd. #3.—

January 9. 1880 From Muhr's Sons, three samples of jewelers' sweeps.

No. 1. 1 lb. av. contains gold 243 grs.
silver 66½ "

No. 2 1 lb. avoid gold 95½ "
silver 31½ "

No 3 1 lb. avoid. gold 181 "
silver 51 "

Rec'd $9.00

January 17. From Orion Co. Arizona.

Sample of argentiferous galena.

Contains Silver, 1598 ozs. per ton.
No Gold.

Rec'd $3.—

January 21. From L. Mayer, Oil City, Pa. (draft of S.N. Lamberton,) seven samples of ore - Tombstone, Arizona
Recd. #21. —

No. 1 Silver, 160 ozs. per ton.
2 48 " "
3 252 " "
4 140 " "
5 257 " "
6 82 " "
7 3056 " "
Trace of gold.

Jany 31. From P.C. Tomson, sample of argentiferous lead ore from Utah.

Contains 73 ozs. silver, per ton.
Trace of gold.

Recd. #3. —

January 31. 1880 From Orion Silver Mining Co.

Ore, A. 60 ozs. per ton. silver.
K. 655 " " "

Pulp A. 237 " " "
" K. 731 " " "

Rec'd. $12.—

Delry b. From S. T. Little, Cumberland Md. through Louis A. Scherr & Co. Phila

Gold Ring; 724 thous. = 17 12/32 K.

Rec'd. $1.—

Delry b. From P. Mockenhaupt, 182 State St. Chicago.
Strip of fine gold — 966 fine

Rec'd. $1.—

February 10. From John C. Blucher, Hillsborough, New Mexico.
Three samples of native gold.

#	Before melting	After melting	Fine.	Silver.	Val.
1.	2.38	2.05	755	240	31.98
2	-.60	-.57	554	440	6.53
3	-.85	-.83	939		16.13

Rec'd #3. —

February 26. From Barnes & Sim, Topeka, Kansas. Sample of ore.

Contains silver, 350 ozs. per ton.
" gold ½ oz "

Rec'd #3. —

March 5. 1880 From W. N. Scothorn, Hannibal, Missouri, a mineral sample.

No gold, nor silver

Rec'd #3. —

March 5. 1880 Gold, amalgam, melted, assayed & stamped; returned to Alexander Hay. Wyoming Terr.

Fineness, G. 806.
S. 125.

		ozs.
Weight - before melting		163.07
	after "	159.16

Value (if deposited) G. 2645.16
S. 20.67
$2665.83

Rec'd $1.50

March 6. From W. N. Crawford, Dayton, Sebastian Co. Arkansas, a mineral sample.

Assayed, & contains no gold nor silver.
Sent $5.—
Returned 2.—
$3. rec'd.

March 11. 1880 From N. B. Nichols, Postmaster, Norfolk Va. a mineral sample. (Chesapeake & Idaho Co.)
Contains 29 ozs. silver per ton.
" " No gold.

Rec'd $3.—

March 12. From Webb & Hall, Janesville, Wisconsin, piece of gold ring.

Fine $742\frac{1}{2} = 17\frac{27}{32}$

Rec'd $1.—

March 17. From H. V. Carter, Central City, Dakota. Three lots.

No gold, nor silver.

Rec'd $15. Returned $6.00, per
6 Dr Le Conte
$9. March 30.

March 24. 1880 From R. I. Holmes, office of R. G. McDonald, East Las Vegas, New Mexico, a small piece of oxide of iron.

Rec'd $5. — Transfered to April.

March 27. From J. E. Briggs, Windsor, Maine, a mineral sample.

No silver nor gold -

Rec'd $3. —

April 8. 1880 Received from the Assayer of the Mint, eighty ~~four~~ dollars 50 cents, the sum of the items for the first quarter of 1880. $84 50

John L. Leconte
Chief Clerk
for Superintendent

April, 1880.

April 3. From P. L. Kuder, Philad^{a}. three samples of silver plate

No. 1. slip, 924.
2 Napkin 924½.
3 Spoon 925.

Rec^{d}. $3. —

April 3. From R. W. Dorphley, (thro' S. Hartranft) a specimen of ore from Arizona.

Contains 5 ozs. silver per ton; no gold.

Rec^{d}. $3. —

April 8. 1880. From A.W. Brinton & Co. Belmont, Lewis & Clark Co. Montana.
Three samples, 1, 2 and 4.

1 one oz. gold per ton
2 19 " Silver "
4 one " " "

Rec'd $9.—

April 10. (Transfered from March 24) Sample of ore from R. J. Holmes, office of R.G. McDonald, East Las Vegas, N. Mex.

Contains gold, 29 ozs per ton. $599.—

Rec'd $5.—

April 12. From W.B. Clapp, Young & Co. 149 State St. Chicago.
A sample of gold.
521, = 12½ kar.

Rec'd $1.—

April 14. From P. C. Tonson, sample of ore from Utah.

Contains 62 ozs. silver per ton. say $68.

Rec'd. $3. —

April 22. From Hon. Saml B. Dick, two mineral samples. Hot Springs, Ark.

Trace of gold; no silver.

May 13. From Simons, Bro. & Co. Phila. a strip of gold.

Fine 553, = $13\frac{9}{32}$ K.

Rec'd. $1. —

May 15. From Charles M. Nes, York. Pa.
Mineral sample - contains no gold or silver

Rec'd $3. —

May 16. 1880 From L. F. Wilson,
Kansas City, two samples of ore.
Rec'd. $10 — returned $4. — (Lyne 2.)
No. 1, trace of gold. No. 2, $10 gold per ton.

May 20. Assay of samples sent by
Morris Ebert, Sec'y Chihuahua Milling
& Mining Co. — 226 Walnut St. Phila.

La Filadelfia,	# 1,	silver	562 ozs.	per ton.
	2	"	52	"
	3	"	45	"
	4	"	283	"
Los Gueyas	1	"	55	"
	2	"	274	"
La Refugio	# 0	"	122	"
	1	"	302	"
	2	"	42	"
San Joaquin de la Prisa	1	"	51	"

2 trace of silver
Special assay, no title — trace of silver.
All of the above contained a trace of gold.

Rec'd. $36. —

June 4. 1880 From A. H. McKelvy, Warren, Pa., two samples of ore from California. (Lock box 152.)

One gives 78 ozs. silver per ton.
The other 27 " "
Trace of gold. (No numbers)

Rec'd #6. —

June 14. From Simons, Roos & Co. Philada — a strip of gold.

Fine 398. = $9\frac{18}{32}$ Kar.

Rec'd #1. —

June 18 - 1880 From W. B. Clapp, Young & Co. two samples of Gold

No. 1 - Fine 570 = $13\frac{22}{32}$ K.
2 " 516 = $12\frac{12}{32}$.

Rec'd #2. —

June 23- 1880 From Carrow.
Bishop & Co.— A strip of fine Gold
Fine 977 = $23\frac{14}{32}$ kar.

Rec'd $1.—

June 30. 1880 Received from the Assayer of the Mint, eighty dollars the sum of the items for the second quarter of 1880.

J. L. Lebaron,
Chief Clerk for
Superintendent

July 2- 1880
From J. N. Davis & Co.
722 Sansom St Phila
2 Samples of Silver Plate.

1 - 929
2 - 929½

Rec'd $2.—

July 13. From Barrow & Bruce, Christiansburg Va. native grs of gold.

650 = ~~$~~ $13.40
703 = 14.50 } per oz

Rec'd $1.—

July 23. From S.E. Brush & Co., Pierson, Michigan - a mineral sample.

Contains no gold, nor silver; also tried for lead, none in it.

Rec'd $5.—

August 13th 1880

Assay of Five Samples of ores for Lieut. W. H. Hugo 9th U.S. Cavly, Fort Bayard N. M.,
Andrew Sheridan 1204 N. 27th St Phila

No. 1 — 11 Ozs Silver per ton
2 Trace "
3 7 Ozs " "
4 2 1/2 " " "
5 21 " " "
Trace of Gold.

$15. Paid.

Aug. 14th 1880
From Simons Bros & Co. a sample of Gold.
Fine — 990 1/2
Rec'd #1.—

Aug 14 — 1880
Two Samples of Chain from W. P Melchen.
1 — 363 1/2 See next page
2 — 550

Aug. 16. Silver chain from W. B. Clapp, Young & Co. 149 State St. Chicago.

Fineness $\left.\begin{matrix} 518\frac{1}{2} \\ 517 \end{matrix}\right\}$ reported 517

Rec'd. #1. —

Aug. 18. From D. E. Mallory, Monroe, Clarion Co. Penn'a. a sample of ore from Arizona.

Contains silver, 24 ozs. per ton; trace of gold.

Rec'd. #3. —

Aug. 18 From W. P. Melcher, Palmer House, Chicago, Illinois. Two chain-links.

No. 1,	$3\frac{1}{2}$,	=	$9\frac{28}{32}$ car.
2	5	=	$13\frac{7}{32}$ "

Rec'd. #2. —

Aug. 21. 1880 From Bailey Banks & Biddle, Phila.
Gold chain-link

Fine 592. = $14\frac{7}{32}$ kar.

Recd. $1.—

Aug. 25. From S. I. Vanstavoren, 1230 Fairmount avenue Phila., on behalf of C. Pike, a sample of galena. Penna.
Contains 3½ ozs. silver per ton.

Recd. $3.—

Aug. 30 From Cyrus Hinchman, Rich Creek, Logan Co. W. Virginia, a mineral sample.

No gold or silver—

Recd. $3.—

Sept. 1. 1880. From D. V. Wemple, Kingsborough, Fulton Co. N. Y., a mineral sample.

No gold nor silver

Rec'd $3. —

Sept 2. From A. S. Tiffany, Gloversville, Fulton Co. N. Y. care of A. Syke, Schenectady.

No gold, nor silver

Rec'd $3. —

Sept. 9. From Alan Wood & Co. 519 Arch St. Phila. a mineral sample.

No gold, nor silver

Rec'd $3. —

Sept. 11. 1880 From Simons, Bro. & Co a sample of rolled gold.

Fine 637½, = 15 10/32 Kar.

Rec'd. $1.—

Sept. 13. From H. B. Parsons, thro' Geo. C. Thompson, 3 samples gold.

No. 1	995
2	995
3	995

Rec'd. $3.—

Sept. 24 From George Eakins, Phila. assay of lead button, from ore.

Makes 15½ ozs. silver, & ⅒ oz. gold } per ton.

Rec'd. $1.—

Sept. 25. 1880 From Simons Bro & Co. Phila. a sample of gold.

Fine 572. = $13\frac{23}{32}$ Kar

Rec'd #1. —

Sept. 28 From E. W. Jones, Phila. two samples of rock.

1 Free from gold or silver
2 Do. do.

Rec'd #6. —

Sept 30 From Jos. A. Caspari, care of C. G. Taylor 109 Ohio St. Sedalia Mo.

No gold, nor silver.

Rec'd #3. —

Sept. 30. 1880 From Henry Mickam, Pamyille, Carbon Co. Penna

No gold nor silver.

Recd. $3.—

Sept 30. From H. Muhr's Sons, Phila

1. Watch case, 318 to 328, or $7\frac{20}{32}$ to $7\frac{28}{32}$ K

2. Button 312, or $7\frac{16}{32}$ K.

$2 paid

Septr. 29 1880 From Dr. C.S. Poley
Two Samples of Qtz from Colorado
Marked Smoky Hill No 1 & No 2

No. 2 - 6 Oz Gold per Ton

No 1. 56 " " " 6 Oz Silver

Recd $6.—

October 9. 1880 Received from the Assayer of the Mint, seventy two dollars, the sum of the items for the third quarter of 1880. $72.—

J. L. Lebaute, Chief Clerk
for Superintendent

October 1880.

Oct^{r} 2. From Booz & Thomas, 108 S. 8th St Phila^{a}

Piece of gold, melted -

Fine 745½, = 17 $\frac{29}{32}$ K.

Rec^{d} $1. -

Oct^{r} 4 From A. J. Canada, Taitsville Ray (R) Co., Missouri

Contains nothing -

Rec^{d} 0. -

Oct. 5. From Simons, Bro. & Co. Phila Sample of gold

Fine 580, = 13 $\frac{30}{32}$ K

Rec^{d} $1.

October 7. 1880 From Thos Sayer, a mineral sample from Colorado.

No gold nor silver.

Rec'd $3. —

Oct. 11. From Isaac Stevens, Lordville Delaware Co. N.Y.

Rec'd $3. — Returned.

Oct 13. From D. S. Criswell, South Oil City, Pa. a sample from Bunkerhill Mine, Tombstone, Arizona.

11.02 gr. silver to the ounce,

670 ozs. to the ton. (Button sent.)

Rec'd $3. —

Oct 16. From S. P. Kase, a button of native gold, for assay.

86 gr. 785 fine. val. $2.90.

Rec'd $1. —

Octr 15. From Wm A. Foy,
Sageville, Hamilton Co. N. Y.
Hornblende, with black lead

~~Recd #4~~. — Money returned.

Octr 16. From Fred. F. Taylor,
Pierson, Michigan.

Contains silver 1998 ounces per ton.
" sold $\frac{1}{2}$ oz.

Recd #3. —

Novem 6. From Simons, Bro. & Co.
Philada. Sample of gold

Fineness 319 = $7\frac{21}{32}$ K.
Recd. #1. —

From Robert Patterson, Phila. gold in
grains from Montgomery Co. Virginia.
Fineness 660.
Recd. #1. — Nov. 6.

1880

Nov. 9. From L. & S. Sternberger 503 Market St; ores from Nevada.

Silver 237 ozs. per ton
Gold ½ " "

Rec'd $3.—

Nov. 9 From S. I. Lanahan, Baltimore a strip of gold for assay.

Fineness 689.
Value of remainder returned, $3.40.
Rec'd $1.00

Novem 18. From Wm Thompson, 3816 Locust St. West Phila— ore from Colorado (for W. Pugh, Penn'a RR.)

Contains gold $88 per ton.
Silver. 1 oz.

Rec'd $3.—

Nov. 26. From J. B. Boatright, Uvalde, Texas, a sample of ore.

Contains nothing of any value —

Rec'd $3. —

Nov. 29. From John H. Campbell, 531 Vine St. Phila. — a mineral for assay.

Contains no metal of any sort.

Rec'd $3. —

Dec. 3. From J. D. Whitham, Valley Iron Ohio Co. West Va. a mineral sample

Contains no gold nor silver.
Rec'd $3. —

Dec. 4. From Hagstoz & Thorpe, Phila sample of silver.
Fine 895½.
Rec'd $1. —

1880

Dec. 7. From Isaac Tucker, West-Laurens, Otsego Co. N. Y., a sample of rock. (Nov. 17.)

Contains no precious metals.

Rec'd. #3. —

Dec. 7. From A. C. Dewey, Pittston, Pa. a sample of galena from "Garden Lode", Clear Creek Co. Colorado. (Nov. 24)

Eleven ozs. silver — trace of gold.

Rec'd. #3. —

Dec 8. — From James Long 203 Church St. Phila. A sample of Ore from Black Hills Dacotah Ty.

Thirty two and a half. Ozs. Gold per ton (32½) — #.670

Rec'd. #3. —

Dec. 28. 1880. From G. W. M. Rigor, Harrisburg Pa., a mineral sample.

Contains nothing of value.

Recd. # 3. —

January 8. 1881 Received from the Assayer of the Mint, forty six dollars, the sum of the items for fourth quarter of 1880. # 46. —

J. L. Lesoute.
Chief Clerk.
Superintendent

1881.

Jany 4. From Smith & Hewitt, a sample of ore from Northern Idaho.

Good trace of gold – say ½ oz. per ton.

Rec'd #3. –

Jany 4. From Samuel Heilner, 314½ Walnut St. Phila. – ores from Colorado.

No. 1. Great Sphinx, Gold 2 ozs. #41.
2. Princeton " 12½ " 8 Sil.
3. Cleopatra Trace of gold. #266.
4. Rocky Mt. Canary Do.

Rec'd #12. –

Jany 6. From Geo. H. Moore, Phila'a Specimen from Zalida mine, Colorado. – Contains gold 3 ozs. Silver 1 oz. per ton

Rec'd #3. –

Jany 8. From S. S. Hartranft, Specimen from Utah.

Contains Silver .775 ozs. per ton.
$3. paid

Jany 13. Hagstoz & Thorpe – silver sample

Fineness 900 ¼

Rec? $1.00

Jany 19. Howell & Bro's 12 S. 6th St. Phila. a sample of ore from Colorado.

Contains Gold 1 3/4 ozs. ($36) } per ton
" Silver 8 ozs. }

Rec? $3. –

Jany. 20 From John Wanamaker a sample of Gold

Fine 487½ = 11 22/32

Rec? $1. –

Jany 25. From John Wanamaker, part of a gold matchcase.

Fine 577. or $13\frac{27}{32}$ K.

Recd. $1.—

Jany 27. From P. L. Krider, Phila. Sample of fine silver.

Fineness 999+ (four assays.)

Recd. $1.—

Feby 1. From Simons, Bro. & Co. Philada. two samples of gold.

No. 1. 984½

2. 214.

Recd. $2.—

Feby 12. From the same;—sample of gold.

Fine 350 — = $8\frac{13}{32}$ K

Recd. $1.—

February 17. 1881. From C. & A. Péquignot, a sample of gold.

Fineness 522 thous. = $12\frac{17}{32}$ K

Rec'd. $1. —

Feb. 25. From De Roy Bros. Pittsburg, Pa. a gold ring.

Fine 616, = $14\frac{25}{32}$ K.

Rec'd. $1. —

Feb. 25. From Carrow, Bishop & Co. Phila. — a sample of gold

Fine 989½

Rec'd. $1. —

March 3 - From Simons Bros.
a sample of Gold.

Fine 969.—

Rec. $1.—

March 8 - From Carrow, Bishop & Co. - a sample of Gold

Fine 992.—

Recd. $1.—

March 11 - From C. D. Cadwallader Penna R.R. 32 & Market Sts Phila
A sample of Ore from Colorado

Contains Silver 19 Ozs per ton
" Gold trace

Recd $3.—

March 17 From Carrow Bishop & Co
A sample of Gold.

Fine 969.

#1. paid

March 29 From H. Muhrs Sons
2 Rings Gold Plated.

No. 1- (Large) contains 3/100 of 1 grain of Gold
" 2 Small. " 28/100 " "
Assay of Watch Case (Gold')
1- .158
2 181
3 170

#8 paid

April 1– 1881 Received from the Assayer of the Mint forty eight dollars, the sum of the items for the first quarter of 1881.–

$48.–

John L. Lebonte,
Acting Superintendent.

April 1– 1881

From Simons Bros & Co
Two Samples of Gold

No. 1– Fine 337
" 2– " 707

$2. Paid

April 4th 1881

A Sample of Ore from E. A. Corbin

Contains Silver 880 Oz per ton
" Gold 2 " "
" Copper 21.6 per cent

$3. Paid

April 21. From Haystos & Thorpe, Phila.
Gold. 990½

$1. Paid
April 14. From Newton Bradley–
Silver bar stamped. 924½.
Recd. 1.50.

April 19.

From Clark & Coombs, North Attleboro', Mass. 4 gilt rings.

		gr.		ct.
No. 38,	contains	0.4	gold, val.	1.72
44	"	0.09	"	0.38
100		0.22	"	0.94
101		0.25	"	1.07

Rec'd $2.— } = 4
" 2 — }

April 20.
From Wm Beeson, two samples of Ore. (Uniontown, Pa)
Nos 2 & 6.—

Free from Gold & Silver

Recd. $6.—

April 22. From Hon. A.W. Leisenring, Mauch Chunk, Penn:
Gold ½ oz. per ton. Silver 2½ ozs. $13.—

April 26- From Hagstoz & Thorpe. A sample of Gold and Silver. (2 samples)

1 Gold. 77 & 78

2 Silver 868.

$2.- paid

19.

April 26- From Hagstoz & Thorpe a small bar for Assay.

Silver 448. Gold 89.-

$1. paid

April 21- From Frank Sell a sample of Gold.-

Fine - 666 or 16 Kar.

Rec'd $1.-

May 2. 1881 From Haystoz & Thorpe, a small cake of base gold.

Contains gold. 141 thous. Two assays.

Rec'd. $1. —

May 2. From W.A. Fry, Hamilton Co. N.Y. - a mineral specimen

Contains no gold, nor silver

Rec'd. $3. —

May 5- 1881. From Haystoz & Thorpe a small bar of Gold & Silver

Contains Silver 584
" Gold 66

$1.- Rec'd.

May 12 From H. Muhr's Sons
Sample of Gold Chain (link.
Fine 557.- " 13. 12/32 K
$1 Paid
May 14. From Hagstoz & Thorpe
a small bar of Gold.

Fine 332.-
$1 Paid

May 17 From James L. Crane
a sample of Ore - Galena
Mineral Hill Mine Lode No 1.
Union Mining district
Summit Co. Colo.
Contains Silver 18 oz per ton
" Gold trace (also 134 oz pr t.)
$3 paid
May 18.- From Simons Bro
A sample of Gold Watch Case.

Fine 561.-
$1 pd
May 26 Sample Simons Bros. 517½

$1 recvd

June 3. - From C. & A. Pequignot
a sample of Gold.

Fine 531 = 12 12/24 Kar
$1. paid

June 3. From W. Haines
A sample of Gold (Jewelry)
Fine 394 = 9 14/32 Kar

$1 paid 35.

June 11 From J. L. Stewart
4 samples of Crushed Ore
Marked A1 A2 A4 B1
A1 Contains 53 Ozs Silver per ton
A2 " 13 " " "
A4 " 33 " " "
B1 " 10 " " "
All contain a trace of Gold.
$12 - paid.
From Andrew McLaurin A sample
of Quartz from New Zealand

Contains Gold a trace say 1/4 Oz pr ton
$3 paid

June 8 - From Andrew Fees
a sample of Ore.

Contains no Gold or Silver

#3 Recd

June 10 From William Robb
Free from Gold and Silve

#3 Recd.

June 11 - From H. Muhrs Sons
a sample of Gold Watch Case

Fine - 263 - or $6\frac{10}{32}$ Kar
#1 Recd

June 18 From H Muhrs Sons
a sample of Gold.

Fine 409 — $9\frac{26}{32}$ Kar
#1 Recd,

June 21 – From H. Muhrs Sons
3 Samples Jewelry

N. 1 –	Fine	409	=	$9\frac{26}{32}$
2	"	414		$9\frac{30}{32}$
3	"	410		$9\frac{27}{32}$

#3 Rec'd.

June 28 From Hagstoz & Thorpe a sample of Gold.
Fine 70 = $1\frac{22}{32}$ Kar.

#1 Rec'd

July 5 From H. Muhrs Sons
5 Samples Gold.

1 –	331
2	390
3	731 ½
4	562
5 –	605

#5. – Rec'd
July 7 – From Hagstoz & Thorpe
Sample of Gold.
Fine 70 – $1\frac{22}{32}$ K.

#1 Rec'd.

July 9th 1881

A Sample of Ore from J. Webb Jr.

Contains 3. Ozs Silver per ton
from J. B. Britton

Charge #3 Rec'd.

July 9- Two Samples of Silver Spoons
from Frank H. Wright
Great Barrington Mass.

1— 899
2 785½

Charge #2. — Fd.

July 11th From A & S. Sternberger a
Sample of Ore from Colorado

Free from Gold & Silver

#3 Rec'd

July 9 From T. Elwood Vail
Summitville. Rio Grange Co Colo.
A sample of Ore.
12 Ozs Silver per ton
3/4 " Gold " "

#3 Recd.

July 11 From Aloy. L Draper
Sutton Junction P.Q. Canada.
A sample of Ore.

Free from Au & Ag.

3 Recd.

July- 2 From J. N. Duff. Big
Stone Gap. Wise Co. Va. A sample
of Ore.
Contains a trace of Gold Say 1/60z.

8 Recd.

July 11- From W. L. Sternbergen
a sample of Ore.

Contains Silver 2 ozs per ton
Gold 3/4 "
$3 Paid

July 21- From H. Muhrs Sons
a sample of Jeweller's Sweep.

Sweep contains 105. grains of Gold
" " 30 1/2 " Silver
per lb. avoird.
Charge $3

July 22 From H. Muhrs Sons
a sample of sweep.

Sweep contains per lb avoird. —

8 ~~6.~~ 1/2 grains of Gold.
3 0. " Silver

Charge $3

July 23rd From Alex. G. Wilson
Fellin City North Park Colorado

Two Samples crushed one.

Contain a Trace of Ag.

$6 Recd.

July 29/01 Assay of Sample of Lead
for C. Russell. Phillips & Jacobs.
Contains Silver 50½
" Gold 1.—

$1 Recd.

Aug. 3 From Morgan & Headly
a Strip of Coppery Gold.

Contains Gold.
397½ or 9 17/32 Kar.

$1 Paid.

July 23- Repto Aug 5

From Tracy C Becker Buffalo.
A sample of Shale Carboniferous

A minute trace of Gold
$3 Rec'd.

July 23 Rep'd Aug 5.

From Joel P. Lines Buffalo

A sample of Shale.

A minute trace of Gold.

$3 Rec'd.

Aug 6 Two samples of rock from
R. S. Staples. Assayed for
Simon Barry Stroudsburg Penn
Free from Gold & Silver

$6 paid.

Aug 9th From R. M. Custer
Fort Sill Indian Ter.

A sample of Rock. —
$3 Paid
Contains no Gold nor Silver

Aug 10. From Joseph F Tobias
a sample of Ore.

Contains Silver 138 Ozs per Ton
" Gold a trace. 1/8 oz.
$3 Paid
Aug 10- From Wm N. Dresher V. P.
Arizona Southern Mining and
Milling Co. Philada. 407 Locust St.

A sample of Ore. Marked
Selected Specimens from Silver Wing
Mine.

Contains Silver 994 Ozs per Ton
Gold a trace.

$3 paid

Aug 1— From Jones & Farrar
Conway Ark.
3 Samples of Rock

Free from Gold and Silver

#9 Reed.

Aug 6— From Dr. E. Pynchon
Buffalo N. Y.
A sample of Schale —

No Gold.
#3 Reed.

Aug 16— D. F. Conover & Co
A Gold Ring

Fine 590 = $14\frac{5}{32}$ Kar

#1 Reed
Aug 19— From J. Zweighaft a
sample of Watch Case
Fine 333 = 8 Kar

Aug. 19- From Rockford Watch Co.
H.P. Holland Sec.
2 - Watch Cases (Silver)

A— 872
B - 902½

$2 —

Aug 24. From J. H. Baldwin, Troy, Pa.
a silver bar. Assayed by cutting each end.
Silver 989½ — Gold 1
Rec'd $1.- per Assay.

Aug. 24/81. From S. Beveiglaft, a
watch case melted down — no loss. Wt. 63 dwt.
No 102607
Rec'd $1 — Fine 334 or 8 K.

Aug (24) From Richd Lindley
a sample of ore.

Contains a trace of Gold & Silver
$3 Rec'd. by Dr. Le Conte

Aug 24 - From Wm H. Drescher.
3 Samples Ore.

1 Discovery Shaft Bevis Mine
Sovereign Group
$\frac{6}{10}$ oz Gold 45 oz Silver

2 - Bevis Mine Sov. Group
1/2 oz gold - 140 oz Ag.

3 - Discovery Shaft. Bevis Mine
Gold trace 7½ oz Silv

#9 Reed.

Aug 25 - From John Folk
a Sample of Limestone

Free from Gold and Silver
#3. Reed.

From O. T Higgins & Son Olean N.Y.
a sample of Ore
a little
Contains Plumbago

Free from Ag & Au
#3 Reed

Aug 30 – From J. N. Davis & Co
932 Sansom St. A sample of Silver

Fine 916

Paid #1 –

Aug. 30 – 1881 – From Wells-Fargo Co.

58 Samples Silver Bars. – 1 for
Gold & Silver. –

Charge $116 Recd.

Aug 31 – From D. F. Conover & Co.
a Gold watch case
melted and Assayed No 136318

Fine 333 or 8 Kar.

Charge $2. –

Septr 3 – From Philip Leslie
Snowville Pulaski Co. Va.
A Sample of Ore.
Contains Iron Pyrites.
Also a trace of Gold.

#3. Recd.

Septr 5. – From Landis & Danser Rushville Ind.
Samples of Ore. From Mine
60 Miles S. of Leadville Colo.
Marked
No. 1 – From the Independence
Contains 30 oz Silver, 6 oz gold
" 2 Galena from the Independence
Contains 68 Oz Silver 1/2 oz gold.
Waiting for Money

Sept. 20 From J. H. Davis & Co.
Two Silver Slips numbered 1 and 5.

No 1 916½
No 5 915

Received #2. –

September 20. From
W. Robertson A sample of Ore
from North Rowe Gold and Silver
Mining Co. Arizona (1130 Walnut St.

Contains Gold 1.10 Oz per Ton
Silver 1/2 " "
$3 Recd.

Sep. 22- From J. H. Davis & Co.
A sample of Fine Silver Granulation

Fine 988 1/4
$1 Recd.

Sep 22. A. Sample of Gold
from R. B. Holden
Providence R. I.

Fine 416 1/2 or 10 Kar.

$1 paid.

Sept. 23 From J. N. Davis & Co.
a sample of Silver.

Fine 916½
$1 Recd.

October 5th 1881 Received from the Assayer of the Mint two hundred and twenty eight Dollars the sum of the items for the third quarter of 1881.

John L. Lebourte
Chief Clerk.

$228.—

October.

W. Dolberry Crockett Texas. #3 Rec'd

Contains Iron Pyrites.
Free from Gold & Silver.
#3 Recd.

October 4th - From C. H. Lynch
Bristol Tenn
A Sample of Ore.
X Free from Gold & Silver

#3. Recd.

October 14th - From Dr. A. E.
Carathers San Antonio Texas.
A Sample of Ore.

Contains Silver 19 Ozs per ton
Gold a good trace $\frac{6}{10}$ Q.

#3 Recd.

Oct 15 - From J. W. Davis & Co

Two Samples Silver Slips

No. 55 925
88 923½

2 Reed.

Oct 19. Silver Sample Napkin Rings

Fine 887½ (Sample all used)

$1.- recd

Oct 20 Silver Sample from John T. Vansant & Co.

Fine 923.-

$1 Recd.

Oct. 22. - From J. R. Timms
Parkersburg W. Va.

A Sample of Sand Stone
free from Gold & Silver

$3 Rec'd.

Oct. 22 From Alex. Allen
Herbert Conecuh Co. Ala.

A Sample of Sand.

Free from Gold & Silver

$3.— Rec'd.

Oct 26 - From John C. Hammonds
Anderson Creek Alabama,
A sample of Rock. —

Free from Gold & Silver

$3 Rec'd.

Oct 31 — From T. Elwood Vail
Forest Hill Harford Co. Md.

3 Samples of Ore. —

No. 1. — Silver 10 Ozs. Gold 1/4 oz per ton

" 2 — " 14 " " 3/4 " "

" 3 " 54 " " 1 1/4 " "

9. Reed.

Nov. 1 — From G. W. Shallcross
664 N. 12 St. Phila — Franklin
+ Pasaca Mine
Two Samples of Ore Georgia

No. 1 — Pyrites 1 3/4 Ozs Gold per ton

" 2. Sand Stone trace "

#6 Reed.

From T. A. Hicks

A. Sample of Ore. Colorado

No. 1 — 167 Oz. Silver Gold ½ oz.

From W. Reeves.

A Sample of Ore "

No. 2 36 Oz. Silver Gold 4½ Oz

#6 Reed.

Nov. 3. J. H. Davis & Co. Silver Slip.

Fine — 925

$1 — Add

Nov. 3. —

Two Gold Rings for M. Rothschild

Cin. O.

No. 1 — 399½

" 2 — 558½

Nov. 5. From Rott Gladfelter
per. G.W. Simpson
a sample of Colorado Sand.
Free from Gold & Silver

#3 Recd.

Nov. 5 Simons Bros & Co.
Two Samples Gold
Nº
No 1 — 550,
" 2 — 403. #2 Recd.

From G.W. Challenor. (664 N. 12th Phila) — Two Specimens from the St. Charles Mines, Georgia. (No 1 — North Side — No 2 South Side)
No 1. Trace of Gold
" "
No 2 " "

#6 — Recd. Nov. 7

Nov 12. Hagstoz & Thorpe – Silver Sample.

June 88 2½ –
Paid 1 –

Nov. – 14 – from Jerome Keely & Co. –
Two Samples of one ,,

No. 1 – Marked Bedded on Slate
Free from Au & Ag

No. 2. ,, Bedded on Limestone.
Free Au & Ag.

Nov. 14 – From J. C. Bunnell & Co. Tunkhannock Pa
Two Samples of Ore

No. 1. Iron Ore
5 6 oz Ag. $\frac{41}{10}$ 6 oz Au

No 2 Rock
Free from Au & Ag

#6 Reed

Nov. 10- From J. O. Miller
New Cumberland W. Va.
A sample of Galena.

Silver 67 Ozs per ton trace of Gold.

#3 Recd.

Nov. 15. From Emmor Walton
A sample of Ore from Sterling
Mine Gold Hill District
Boulder Co. - Colo.

Contains 31½ Ozs Gold per ton.

Nov. 19. From Central Indiana and
Cimmeron G. & S. Mining Co
Thornton Ind. Geo. Coulson
Free from Gold & Silver.

#3. Recd.

Dec 9th From J. C. Creighton
A sample of Ore

Contains 14½ Oz Ag per ton
Au Trace

#3 Recd.

Dec. 9- Assay of Sample of Galena for Chas. Buckland

Contains Silver 83 Oz per ton

Lead. 74 3/4 per cent

From W. W. Armstrong
Williamsport Penna

A Sample of Ore.

3 Oz Silver per ton

#3 Recd.

Dec. 10 - From Counties & Cox
Waldron Scott Co. Ark.

A Sample of Ore.

Contains Iron Pyrites.

Free from Gold & Silver
$3 Recd.

Dec. 12 - From Geo. Coulson
Thorntown Ind.
Sample of Ore. Crushed
Marked Smugler Lode No. 1 -

Contains 162 Ozs Silver per ton
39 " Gold " "

Re Assay of J. T. McKim Lode.
Contains Gold. 64 Ozs per Ton.

$3 Recd.

Dec 20 - From Samuel Jones
Wind Gap. P.O.
A sample of "Ore".
Free from Gold & Silver

$3 Recd.

Dec 22 - From Hagstoz & Thorpe

A sample of Gold

Fine 130. →
Rec'd $1 -

Dec 15 From E. Gaffen
Danville Iowa.
A sample of Ore.
Qtz & Iron Pyrites

Free from Gold & Silver

$3 Recd.

Dec 20 From J. W. Heydrick Bradford Penna.

A Lot of Rocks.

Free from Gold and Silver

$3.—

Decr. 27— From E. P. Carpenter 113 S. 4th St. Phila.

A Sample of Ore.— "Turkey Creek" Arizona

Silver 138 Ozs per ton Gold. 3/4

$3

Decr. 27— From Geo. Coulson Thorntown Ind.

Sample of Ore.— J. T. McKim Mine

Free from Gold & Silver

$3 Recd.

Dec 30 - From
A sample of Ore Arizona
Chas E. Darragh
A trace of Gold.

(Fine. of Grain 782 - 832

$1.00

Oct.

January 11. 1882. Received from the Assayer One hundred and eight Dollars, the sum of the items for the fourth quarter of 1881.

$108.-

J. L. Lebonte,
Chief Clerk.

January 24 1882

From H. Dunham
Glen Aubrey Broome Co N.Y.

A Sample of Rock

Fossil limestone, free from Au & Ag

#3 Reed.

From Patrick Lynch.

A Sample of Ore New Mexico

2 Ozs per ton Au. 1 oz Ag.

#3 ~~Reed.~~

Jan 5 — From Chas. O'Neill
A Sample of Ore. Ltg.

A trace of Gold.

$3 Recd.

Jan. 10 — From. Chas. E. Darrach
Two Samples of Ore.

No. 1 — Marked Eclipse
Silver Glance.

Contains 118 Ozs Silver per ton
" 1 3/4 " Gold " "

No. 2. — Ltg.

Contains 21 Ozs Silver per ton
1 3/4 " per ton.

$3 Recd.

Jan 16 - From John Wanamaker
A gold ring.

Fine 730 - or 17. 17/32 Kar

#1 Fd.

Jan 18. From E. G. Fay
3609 Locust St. Phil.

A sample of Gold Grains. - native

Fine - 635 - 637. av. - 636
Silver — 342

Jan. 18— James Lynch
(Lead Ore)
Elizabethtown New Mexico
Contains 18 Oz Silver per ton
6¼ " Gold "

$3 Paid.

Jan 21 From L A. Kotzow & Co
A sample of fine Gold.
(W. H. Hansell Agt Phila).

Fine 975 ½ or 23 13/32 Kar

$1 paid.

Jan 25 – From Chas G. Darrach

~~Five~~ 4 Samples Ore.

1. Marked Daisy.

1½ Oz Silver Gold trace

2. Marked Cap Fork

A trace of Gold.

3. Marked Copper Glance Claim
1 oz Silver per ton

4 – 4 Oz Silver Trace of Gold

X ½ Oz. Silver Copper about 30

$12 Rec'd

Jan 25 - From Isaac Cade
Pagosa Springs Colo. V 1

Three Samples of Ore.

No. 1 - 2. 3.
No. 1 - & 3 A trace of Gold.
No. 2 Free. -

$9 Recd.

From E. C. Bickel. -
Elkhart Ind.
Three Samples. 1 - 6 - 2

No. 1 Lead Contains 15 7/4 Oz Silver pr ton
" " 4 " Gold.

No. 6 Copper trace of Gold

No 2 Bullion - 4 Oz. Silver
trace of Gold.

$3 Recd

Jan. 28/82. Assay of Sample of Rolled Silver from Northwestern Watch Case Company, Rockford Ill.

Fine — 861 —

Rec'd $1.—

Balance of Sample returned with certif. per Exp.

Feb. 1— From H. G. Gill
Sample of Watch Case (Gold.

Fine 329

$1 Paid

From Peerless Organ Co.
Two Samples of Ore. Marked
No. 1— D. L Gaylord Wyalusing
Bradford Co. Pa.

Contains 10½ Oz Gold per ton

No. 2— A trace of Gold

$3 Rec'd.

Feb-1st 1882.

Silver Sample for J.H. Davis & Co.

Fine - 924½

#1 Reed

⅛ Assay of Gold Ring for N. Newlin's Sons.

Fine 324 —

Charge #1. — rec'd.

Feb. 14 From Simons Bro. & Co

Sample of Gold. —

Fine 486½

Reed #1. —

Feb. 14 From Geo B. Hall

(Fort Worth) Texas

A Sample of Ore.

2.56 oz Ag. (trace

#3 Reed.

From Dr. Izard & J. N. Applegate

Two Samples of Ore. - No 1. Brown 2 Black

A trace of Gold & Silver

Feb. 20 - From L & S. Sternberger
A Sample of Ore.
Iron Pyrites.
Contains a trace of Gold

#3 Recd.

From Harned, Jacob & Co.
A sample of Ore. Pyrites.

#3. Recd.
7 Oz Silver
9/10 " Gold.

From G. A. Shallcross Sample
of Ore (Georgia) fr. J. M. Creighton
2 1/2 Oz. per ton.
#3. Recd.

Feb. 25 - Simons Bros & Co.
Two Samples of Gold.

No. 1 - 565

No. 2 392

$2 Recd.

March 2 From Chandler & Shrader
41 Gold Rings. - (Chicago.

No 1 -	404	9	$\frac{22}{32}$	Kar
2	390	9	$\frac{16}{32}$	
3	408	9	$\frac{25}{32}$	
41	705 $\frac{1}{2}$	16	$\frac{30}{32}$	Paid $4. -

March 6. Schirr from Napoleon Ohio
Fine 872
Recd $1. -

March 8. From E. C. Bickel (Elkhart Ind) a sample of iron matte

Contains 65 Oz Silver per ton
Au a trace
$1. - paid

March 15 - Thomas G. Brown & Son,
A sample of Gold. (granulated)
Fine 990 ½

#1 Reed.

March 16 Base Bullion, chiefly lead
from S. C. Griffitts, Texas. — from
Breckenridge. Colorado.
Silver 459 Ozs.
Gold 17½ "
Received #3.—

March 14 - From Delos Rockwell
Troy Bradford Co. Penna
A sample of Ore. — Texas
Gold. 3½ Ozs. per Ton.
#3. Reed.

March - 20 - From John L. Gaylord Wyalusing Penna A sample of Ore.

Contains 16 Oz Gold per ton

#3 Recd.

March 20 - From Dr Izard Two Samples Copper

No. 1 - 16 parts Gold per 1000

2 1 " " "

or No. 1 - 466 Oz gold per ton of Cu.

" 29. " " " "

March 20 - From J. C. Warner Nashvill Tenn. A sample of Ore (from J. B. Brittain)

A trace of Gold.

March 21 – Piece of Silver from Hapstay & Harper – 88 7½ fine.

$1 R.

March 21 From Fred Fette Little Rock
A sample of Ore,
7 Oz Silver per ton Au trace
$3 Reed.

March 23. From Philip F. Fulmer
Dingmans Ferry Pike Co. Penna
A sample of Ore,
Free from G & S,
$3. Reed.

March 25— Ezra Lakens Phila
A sample of Ore

Contains 189 Oz Silver per ton.
A trace of Gold

$3 Recd.

March 27- Hagsty & Thorpe
a sample of silver

fine 881/2

Rec'd $1—

March 27- Sample of Ore
L.R. Snowden.—

Gold. 105 Oz per Ton
Silver 17 " "

$3

The Mint of the United States,

AT

PHILADELPHIA, PENN.,

Assay Department, May 14, 1881.

Sample of Gold (native)
from North Carolina.
Value estimated for Isaac Tull.

Estimated Value of gold
contained in lump.
$66.96.

Jacob B. Eckfeldt
Act. Assayer

The Mint of the United States,

AT

PHILADELPHIA, PENN.,

Assay Department, ..., 188

Killie Lode Owl Gulch
Hinsdale Co. Colo

1 1480
2 " 44

Watson Lode Engineer Mtn.
Galena Mining Dist
Hinsdale Co. Colo

1 } g ✕ S 4½ ½ g
2 } 5 1 troy
3 g 1½ 5

Arnold Bertels
Wilkesbarre
Pa

The Mint of the United States,

AT

PHILADELPHIA, PENN.,

Assay Department, ..., 188 .

Percentage of Lead in Samples of Ore.

Forest. No.	1	68 per cent lead.
	2	69 " " "
	3	65 " " "
	4	19 " " "
	5	but little lead, not sufficient ore for assay
Little Smokey	6	72 " " "
	2	57 " " "
Buckeye	1	55 " " "
	2	56 " " "
Chance	1	58 " " "
	2	12 " " "
	3	11 " " "

Jacob B. Eckfeldt

Assayer.

The Mint of the United States,

AT

PHILADELPHIA, PENN.,

Assay Department, November 17th, 1882.

Assay of twelve samples of Ore - for
Hon. H. G. Fisher, Huntingdon Pa.
Sample marked Forest.

No. 1- Contains 34 Oz. Silver per ton = Gold 3/10 Oz. per ton
2 " 57 " " " " " 25/100 " "
3 " 37 " " " " " fair trace.
4 " 17 " " " " 2/10 Oz per ton
5 " 1 " " " " trace
Little Smokey
1 " 32 " " " " 15/100 " "
2 " 26 " " " " 2/10 " "
Buckeye.—
1 " 29 " " " " 1/10 " "
2 " 40 " " " " tr.
Chance
1 " 46 " " " " 1/20 " "
2 " 12 " " " " 3/10 " "
3 " 26 " " " " trace

610 - 617
600. - 617
481 - 476

608½ 605
615 - 609½
511 - 533.

614 - 615
650 - 641.
581 - 582

610

The Mint of the United States,

AT

PHILADELPHIA, PENN.,

Assay Department, ..., 187 .

14.20 - 14.26

14 13 14.26
~11 - 17 11 - 13

14 19 14 17
14 24 14 20
12. 8. 12 25

14 23 14 24
15 19 15 12
13 30 13 31

1- Grs

80.4 grain

2 58.5

3 - 84

80.5
59.5
84.

59.5
998 7
476 8
535
5355
59381 0

80.5
998
6440
7245
72450
80.339 0 1

84
998

187

United States Mint, Philadelphia, Penn.,

ASSAY DEPARTMENT,

Mahr

1 — 617.

617.5

476.

605

609.5

533.4

615.5

64[redacted].2

582

620

1290

March 27- From T. Elwood Vail
Summitville Rio Grande Co. Colo
Two Samples of Ore.

No. 1- 5 Oz. Silver per ton $\frac{2}{10}$ Oz Gold
" 2 3 " " " " $\frac{1}{10}$ "

$6.R.

April 4- From Geo Eyster
two Silver Spoons

1- Fancy — 925
2 Plain 921

$2 Reed.

April 5- From B. F. Norris & Co.
Sample of Gold Chain Chicago.

Thick — 496
Thin 470

$1.—

April 5 From F. Fette
Little Rock Ark.
Sample of Crushed Ore.

5 Oz Silver per Ton
1/10 " Gold "

$3 Reed

April 11- From W. C Gill. a
Sample of Gold Watch Case.
fine 1024 9-22 Kar

$1

April 13- From John A.
Blackburn Van Wert, Van Wert Co. Ohio
A sample of Ore Crushed,
from Laura Mine of Tyndall
Mining Dist. Pima Co. Arizona

Contains 9.75 Oz. Silver per ton
a trace of Gold.

$3

From Chas. J. H. Ganter Manchester Md. – A sample of marked Gold-dust. – Weight. 96 grains or 6.250 Mg. grams. contains 80 M.g or 70 M.g. Silver 10 gold

or 1 ton of dust contains 46.6 Oz Gold per ton
326 ~~343~~ Oz Silver
$1

From Hagsto & Thorpe A sample of Silver
Fine 894.–

$1 Recd

J Hoard & Co Apl. 24/82
Silver = 915.
$1. Recd

J. H. Davis & Co. Apl 27

Silver 92~~4~~

Rec'd $1–

May 1 – From W. P. Miller
Melrose Cal. –
Castle Dome Mining & Smelting Co.

Sample of ore.

Contains 2850 Ozs. Silver per ton
a trace of Gold.

$3 R.

May 1 – From P. L. Krider
A sample of Silver 925

Rec'd $1. –

May 1 From Joshua Williams
Petries Corners. Lewis Co N. Y.
A Sample of Rock

Free from G. & S

$3 Recd.

May 4— From T. Halliday
Jonesville Va.
A sample of Rock
Limestone Free from G. & S

$3 Recd.

May 5- From Simons Bros No
Sample of Gold.—

Fine 985.—

$1 Recd

May 4- From W. E & C. P McVicar
Wytheville Va.
Red Oxide of iron Free from
Gold & Silver

$3 Recd

May 8 – Saml. R. Hilt & R C Bell.
a sample of Ore.

A trace of Gold.

#3 Recd.

May 9 – From G. W. Shallcross
two Samples of Ore. – Franklin
& McDonald Mining Co. Geo.

1 – A trace of Gold
2 – 3¼ Oz " ton.

May 10 – From J. F Baker &
J. T. Wolf. Seymour Baylor Co. Tex.
Three samples of Ore
1 Iron Pyrites free from Au & Ag
2 "
3 "

#5 Recd.

May 13.– From Mrs. Hill
Two Samples of Ore.–
No. 2 – "Exchange" free from Au & Ag

No 3.– "Great Eastern" a trace Au.

May 13 – Two Gold Medals.–
(Chester Co.) –
Fine 988 – & 998.–

$1 Recd.

May 16 B. S. Banks 705
Chestnut St,
Sample of Ore.–

Gold 1/12 oz per ton

$3 Recd.

May 15 — From
C. N. Harrison Cairo
Ritchie Co, W. Va. —
A sample of Ore

free from Gold & Silver

May. 26 — 1882 From
C. O. Davis Independence
Grayson Co Va. —

Sample of Ore —

A trace of Gold
#3 Reed. Rept to Supt.

May 27 — From N. E. McWane
Wytheville Va.
A sample of Ore

a slight trace of Gold

#3 Reed

May 29. From John F. Porter
Lay Routt Co Cole

A sample of Ore. #1 Reed.
on hand.

June 1 - From H. Thomas Phila
A sample of Gold —

Fine 566 value 11.70 per g.

#1 Reed

June 3 - From Eleazer Thompson.
Danbury Con.

A sample of Ore. —

Free from G. & S.

#3 Reed.

Shallcross — Amt. — Bar. G. 359½
C 604.
#1 Reed.

June 16 — 1882 — From Thos G. Brown & Sons. 1 Bond St. N.Y.
A sample of Gold —
Fine 743 or 17. 27/32 Kar

#1 Rec'd

June 22. — From Louis Duenweg Terre Haute Ind.
4 Samples of Bullion (Leady)

T. Taubneck Ironstone, — A trace,
X " Gravel. 23 6/10 Oz. Silver & 6/10 " Gold "
V. Virginia A trace of Silver
Pieces — Omega 5 1/2 Oz. Silver
trace of Gold.

#4 Rec'd.

July 10th Simons Bro & Co.
Sample — Gold 136 fine.

1. Rec'd.

United States Mint, Philadelphia, Penn.,

ASSAY DEPARTMENT,

From 1882

Macipil Mexico. two samples

1 Espiritu Santo — 138

2 Dulces Nombre 48

R. W. Silvey.

Silvey House

New York.

Cor Bway & 29th

Received #6.

July 12 H. G. Gill 610 Chestnut.
Gold Sample - 284 fine
#1 - accepted

7/14 Simons Bros & Co. ~~XXXX~~ Sample Bullion
Silver 860 - Gold 3
#1.00 received

From R. W. Silvey
Gilsey House
N. Y.
Two samples of Ore. Mas-ipil Mexico
1- Espiritu Santo 138 Oz per Ton
2 Dulces Nombre 48 " "

#6 Rec'd

July 29 - From James Prince Medea
Ore Mexico (~~Malinta~~ Mapini
Sample of Crushed Ore. - Mapini
Contains 1690 Ozs per ton

Aug 11 – Simons Bros
Sample of Silver
Fine 647½

$1

Aug 12 Sample of Gold
Carrow Bishop & Co.

Fine 522
$1 R.

Aug 13 – J. Stackhouse Albany
Sample of Gravel & Rock
Free from Gold & Silver
$3 Recd

Aug 15 – Carrow Bishop & Co.
A Sample of Gold Chain –

Fine 528
$1 Paid 528

Aug 15 – N. Muhrs Sons A Sample
of Gold ring
Fine 746½

$1 Paid

Aug 16— W. N. Bucklin
A sample of ore Colorado
Free from Gold & Silver

$3 Rec'd.

Aug 18— Simons Bros & Co.
A sample of gold

Fine 424 = 10 6/12 Kar
Rec'd $1.—

Aug 18— From Chs. M. Betts
4 Samples Rock

1
2
3
4 } Free from Gold & Silver

Aug 21— From Selser & Brother A
Sample of Ore.— Lead
320 Ozs Ag. per ton
Au trace

$3 paid. lead about 11 p.c.

August 22 Began Letter from Hamilton Diesinger.

Fine 920

#1 rec'd

Aug 23 – Hagstoz & Thorpe
3 Samples Gold –
1 20½ G 879 Silver
2 1 G 899 Silver
3 ~~899~~ (900)

#3 Received.

Aug 23 – H. Muhrs Sons.
Gold watch Case.
2.19 Ozs. after melting
Fine ~~#0~~ =
" .115½ Contains 121.4 grains
Pure gold. (121.4 grains
Receipt #1.

---

824. Caron, Bishop & Co. Gold Chain

Tare 567.8 (Rep 567½

#1 Paid

1882

8/23 Hamilton & Diesinger
Assay — (cut) 926
Granulation — 989.
$2.- Recd

8/26. C. H. Wenhold — Gold Ring.

Fine 725½ = 17 13/32 Kar

$1 Paid.

Aug 27 — Assay of Sample of Ore — marked Concentration Assayed for Mr. F. Stuart —

Silver 5. Oz per Ton
Gold 0.6 " "

Sep. 5 — " C. H. Wenhold Gold Ring. —

Fine 757 = 18 5/32 Kar

$1 Recd.

Sept 4— From T. W. Higgins
Olean. N.Y. Two Samples of Ore
Smaller lot No. 1
Larger " " 2
Free from Au & Ag.
" "
#6. Recd.

Sept 2— From Henry C. Moyer W. M.
A Sample of Rock Bucks Co.

Free from Gold & Silver
#3 Recd.

Sep 9— From C. H. Wenhold
Ring (Gold)

Fine 743 — 17. $\frac{27}{32}$

#1 Recd

Septs 11— From Bitterman Bros
Two Gold Rings.
No. 1- Marked 18 Kar - Fine 706½

No. 2 " Solid Gold. - Fine 437½
$2 Rec'd

Sep 13 - V. Mukris Sons. A
Sample of Gold

$1 Rec'd

Sep 13 - From Shreve Crump &
Low + Boston. A Silver Spoon
Fine - 930.—

$1 Rec'd

Sep. 12 — Ore - for
Thos. McCabe. Troy Pa
Ore from Georgetown Texas.

10% Gold per Ton

$3 Rec'd.

Sep 14 — H. Muhrs Sons
Sample of Gold.

Fine 581 — a 13 39/42 K

#1 Recd.

Sep 26 — Simons Bros & Co
(1) Sample of Gold
Fine 215½
(2) Sample. Silver 755 Gold 4.
#2 Recd.

Oct 2 — H. Muhrs Sons
a Gold watch Case.
Fine 145 —
Contains 153 3/10 fine Gold.

#1 Recd.

Boston

Oct. 4 - From Bigelow Kennard & Co.
Four Samples of Gold.
No 1 - 564½
2 563½
3 562

Oct 5 - From F. Muhr's Sons
Plating from Watch Case.
.51 before .50 Oz. after melting

Fine 63 7½ or 15 9/32
#1R

Oct 7 Silver Bracelet - Solon Wanamaker
Fine - 547½
Rec'd #1 —

Assay of three samples of Gold Grain for W. M. Fisher & Co. Providence R. I.

No. 1	393
2	411
3	527

#3 R

Oct 11 – From Hamilton & Diesinger
A Silver Granulation
Fine 989¼
Received #1.

Oct 10 – From E. C. Monk
Stoughton Mass.
A sample of Galena
Contains 5 Oz Ag per ton
#3 Paid

October 18 — From R. B. Holden
Providence R.I. — A sample of Gold

Fine 413½ or $9\frac{29}{32}$

#1 Recd.

Oct. 20 — From Wm M Fisher & Co
Providence R. I.
A sample of Gold. —

Fine 996

#1. R.

Oct 23 R. B. Holden & Co
Providence

Sample of Gold — Fine 988

#1 R.

Oct 23 — For H. Muhrs Sons two samples of Gold.

No. 1 Marked 10K Fine 406 or $9\frac{24}{32}$
2 " 12K " 478½ $11\frac{15}{32}$

#2 Red.

Oct 26. Silver Bracelet — J. Wanamaker
Fine 749.

#1 R.

Oct 28 — From J. G. Brown Sons N. York
A Gold Ring
Fine 575 or $13\frac{25}{32}$

#1 R.

Oct 28 - B. F. Norris Chicago
3 Samples Gold
1 Fine 453
2 " 468
3 " 517
#3R.

Oct 30— Two Samples of lead
No. 1 Lead — 256 Oz per ton G. B

" 2 Drops 210 " " " 2
#2 R.

Oct 31— From Simons Bros & Co.
two Samples Gold —

No. 1- Link — 519
2 768- 822 - 784½

#2 R.

Nov. 2— From Jas McCurdy
Black Hills — A sample of
Ore. —
S 1½ Oz. per ton Gold
½ " Gold
#3. —

Nov 6- From G.W. Shallcross
two samples of Ore.

No. 1- 1/2 Oz Gold per ton
2 1/4 " " "
#3 R

Nov. 6- 2 assy from T.C. Bailey
Fine 85 0

#1 R.

Nov 10 From Tatum & Bro
4 Samples Lead & Drosses
P. M. & S. Co.

No. 2	202 Ozs Ag per ton bullion	L	
"	12 " " " "	D	
3	19 5 " " " "	L	
"	14.6 " " " "	D	
4	191.6 " " " "	L	
"	20.8 " " " "	D	
5	183. " " " "	L	
"	19.3 " " " "	D	

Gold. 34.25 .32 .25
.02 .02 .02 .02

Nov. 14 – Phila. M. & S. Co.,

6 –	202½	Oz.	Sil. per ton	L.
6	131.	"	"	Drs.
6	192½	"	"	L.
7	101	"	"	Drs.
6 –	.25	"	Au. "	L
6	.20	"	" "	Drs.
7	20	"	Au "	L
7	10	"	" "	Drs.

No 6 – L. 91 g. 7 L. 101.9
D. 13.75 – Drs. 11.6

Nov. 15. – Two samples of Ore
H. G. Sickel. —

No. 1 – 2¼ Oz Gold per ton
2 – 1¼ " " "

6.R.

Nov 15 – W. S. Comly Port Chester
N. Y. A Sample of Ore
A trace of Au & Ag.

3 R.

Nov. 16 – L. W. Reid
Va. Midland R. R.

Free from Au & Ag.

(waiting for money)

A. W. Garrow.
Colo.

2 Samples. – Free from Gold & Silver.

$6. Recd.

Nov. 22 – B. R. Tubbs M. D.
Alco Stone Co. Ark

Limestone with iron pyrites
free from Gold & Silver

$3 Recd.

Nov. 23- Robt. Robertson
Qtz. North Star Mine Amador Co Cal.
To 118 S. Front St.

Gold 3/10 Oz per ton.

$3 R.

Nov. 23- H. Muhr's Sons
Two Samples of Gold.

No. 1- 486
2 410

$2 Rec'd.

---

27 David T. Burr. (Britton.

A Sample of Ore - Galena.
Silver 19 Oz pr ton. Gold 1/20 Oz. p ton
lead. 65 percent.

$8

---

29. Phila. M & S. Co.— Lead Matt
521 Oz Silver Sifting .28 Oz. Gold Sifty
112. " " Scale. .08 " Gd. Scale

$2

Jas. Steinau & Co. Cincinnati O.

A Gold Watch Case.

Fine 307 7 - 12/32 Kar

#1 R.

Dec 9- R. B. Holden & Co. Providence R I.

A Sample of Gold.

Fine 389½

#1 R.

Decr. 11- Jas. C. M. Castland

Chicago Ills.

A Silver Watch Case.

1 - 894 outside rim

2 896 centre "

3 901 lid

#3 R

Dec 15 - H. Muhrs Sons.

Sample of Gold.-

Fine 527.- 12 21/30 K.

#1

Dec. 15- Three Samples Ore. J. N. Kerns
1- 192 Oz. Ag Gold 3/10
2 322 " " "
3 642 " " "
#9 Reed.

Dec 19. H. Muhrs Sons Sample
Fine- 537½ 12 28/32 K
#1 R.

Dr 19 From Joseph Pellet.
A sample of Ore-
3¼ au Ag 2
Gold 3¼ Oz per ton Ag 2
#3 Reed.

Dec. 22 Simons Bros & Co. 2 Samples Ore
No. 1- Slip.- 2162
2 Cutting 2221
#2 Reed.

Dec 22 H. Muhrs Sons. — Sample
Au. Fine 533
#1.R.

August 12 Dollar —
413.2 920/4
Equiv returned.
U.S. $.

The Mint of the United States,

AT

PHILADELPHIA, PENN.,

Assay Department, Dec 23, 1882

Sample of Gold. Simons Bros & Co

Fine 570.—

#1 R.

Dec. 26— R. B. Holden Providence R. I.

a Sample of Gold. Fine 398.—

#1 Reed.

Dec 28— J. P. Giles. Richmond Va.

Sample of Ore free from Gold

#3 R.

H. Mulvs Sons. — Gold. Fine 566½

---

709 Walnut

Dec 29— N. E. Van Sickel. 2 samples ore

#6 Reed.

Dec 29 G. A. Shallcross
Two Samples Ore. —
No. 1 — Sulphurets — free from Gold
No. 2 (Copper blue) 2 Oz Gold per ton
$6 R.

Dec. 29 — W. N. Finley
Phila. — Sample of Ore
$3 Rec'd

April 8. 1880

Dollar. 412.5 gn. 899½.

J. L. Leb. Equivt. returned

April 22. Eagle 258.0 gn. 899.3. Sil. 7.

J. L. Leb. Equivt. returned

May 10. Dollar, 413.3 gn. 900.0

J. L. Leb. Equivt returned

May 20. Eagle 258.2 gn. 899.4. Silv. 0.6

J. L. Leb. Equivt returned

July 12 Dollar 412.2 grs. 900.¾

J. L. Leb. Equivt returned

Aug

1879

Dec. 12. Dollar, 412.7. 899.0

J. L. Leb. Equiv. returned

Dec 31. Eagle 258.3. 899.9

J. L. Leb. Equiv. returned

1880.

Jany 13. Dollar, 412.5. 900.5

J. L. Leb. Equiv. returned

February 9. Dollar 412.6 8984

J. L. Leb. March 12th. Equiv. returned

March 8. Dollar 412.2. 900.0

J. L. Leb. Equiv. returned.

The Mint of the United States,

AT

PHILADELPHIA, PENN.,

Assay Department, October 5, 1882.

Received from the Assayer of the Mint Fifty three dollars, the sum of the items for the third quarter of 1882.—

$53.— S. R. Cowperthwait

Chief Clerk

1879

		gn.	G.	S.
Sept. 4.	Double Eagle.	516.02.	899.9.	10.–
	(Coinage of August.)			

J. L. Leb. Equiv^{t}. returned.

		gn.	
Sept. 9.	Dollar.	413.4.	899 3/4.

J. L. Leb. Equiv^{t}. returned

Oct. 10	Dollar	412.6.	901/4

J. L. Leb. Equiv^{t}. returned

Nov. 11.	Dollar	412.4	899/4

J. L. Leb. Equiv^{t}. returned

Dec. 1.	Double Eagle,	516.	899.6

J. L. Leb. Equiv^{t}. returned

Assayers Report for the first quarter of 1881
of Assays of Ores filed &c, and moneys rec'd
therefor

Total $48

Settled with Supt. as per his rect. for $48.

1882 3 – $53

March 14. 1879

		Grs.		G
Feb. coinage.	Dollar.	411.3	900 1/4	0.3
March "	"	412.1	899 3/4	0.4

April (Equivalent returned.)

April 15.

				G
April 15	Dollar	412.5	898 3/4	0.5

(Equiv. returned)

		grs		G
May 12.	Dollar,	413.4.	899 1/4	0.5

J.L.Leb. (Equiv. returned.)

June 5. Dollar 412.9. 901.
J.L.Leb. (Equiv. returned)

July 22. Dollar 412.2. 898 3/4
J.L.Leb. Equiv. returned.

July 30. Double Eagle 516.18. 899.2
(3 assays.) Silv. 9.5
J.L.Leb. Equiv. returned

Augt 11. Silver Doll. 412.4 900½
J.L.Leb. Equiv. returned

121

5 5
7 4
2) 3 2 9
1 6 4

P. M. & S. Co. No. 7.
Lead 101.9 ℥
Ores 11.6 ℥